

# BARITAINER® CHEMICAL RESISTANCE TABLE

<b>E = Excellent</b>
<b>G = Good</b>

Acetic Acid	G	Isopropanol	E
Acetone	E	Ketones	E
Benzene	E	Linseed Oil	E
Brake Fluid	G	Lubrication Oil	E
Butane	E	Methane	E
Chlorobenzene	E	Methanol	G
Chlorodefluoroethylene	E	Methyl Ethyl Ketone	E
Chlorodefluoromethane	E	Methyl Glycol	G
Citrus Oil	E	Monochloroethyl Acetate	E
Cyclohexane	E	Monochromomethyl Acetate	E
Cyclohexanol	E	Naphthalene	E
Cyclohexanone	E	Nitrobenzene	E
Dichlorobenzene	G	Paint Solvents	E
Dichloroethane	G	Palm Oils	G
Dichlorofluoromethane	E	Parafin Oil	G
Dichlorotetrafluoroethane	E	Paraxylene	G
Dioxan	E	Phenol	E
Edible Fats & Oils	E	Polyglycols	E
Ethanol	E	Propanol	G
Fats & Waxes, edible	E	Pyridine	E
Fatty Acids	E	Shellsol A/AB	E
Fatty Alcohols	E	Silicone Oils	E
Fruit Juices	E	Solvesso 100/150	E
Gear Oil	E	Sulfolane	G
Glycerol	E	Terpenes	E
Grease	E	Tetralin	E
Heptane	E	Thinner	G
Hexachloroethane	E	Toulene	E
Hexachlorobenzene	E	Trichloroethylene	E
Hexane	E	Trichlorotrifluoroethane	E
Hydraulic Fluid	E	Triethanolamine	E
Hydraulic Oil	G	Turpentine	G
Ink	E	Xylene	E

Data are based on a concentration of 4% Kortrax® BR and testing at 25°C. We recommend that users perform specific tests and comply with applicable laws and regulations.

Data on this table are based on current knowledge and experience. Due to the wide variety of possible influences during the use of our Baritainer series this information does not exempt the user from conducting individual tests. No legal guarantee or obligation may be inferred from this information, whether for specific properties or for suitability for a particular application. It is also the sole obligation of the user of our products to verify compliance with the applicable laws and regulations.